

B 1

Classification	Insulating Brick JIS R 2611 Group B1		
Physical Properties	Max. Service Temp.	°C	900
	Bulk Density	kg/m ³	680
	Cold Crushing Strength	kg/cm ²	27
	Modulus of Rupture	kg/cm ²	10
	Permanent Linear Change After Heating at 900 °C	%	-0.90
Chemical Composition	Alumina (Al ₂ O ₃)	%	8.0
	Silica (SiO ₂)	%	56.0
	Lime (CaO)	%	33.0
	Iron Oxide (Fe ₂ O ₃)	%	0.5
Thermal Conductivity	at 350 °C	W/m.K	0.15
	at 400 °C	W/m.K	0.16
	at 600 °C	W/m.K	0.17
	at 800 °C	W/m.K	0.18

The above data are typical values of which the properties of the samples tested according to the internal procedure and standard of Siam Refractory generally accepted by our customers for many years. The above data can not be used for specification or guarantee purpose. Siam Refractory reserves the right to update the above data and change our internal procedure and standard without any prior notice.

THE SIAM REFRACTORY INDUSTRY CO., LTD.

1 Siam Cement Road, Bangsue, Bangkok 10800 Thailand Tel. (+662) 586-3246-52 Fax. (+66 2) 586-2982, 587-2149

